4 5 6

#### 7 8

## Deformation Characteristics of Aluminium Composites for Structural Applications

Theodore E. Matikas<sup>1</sup> and Syed T. Hasan<sup>2</sup>

<sup>1</sup>Department of Materials Science and Engineering, University of Ioannina, <sup>2</sup>Faculty of Arts, Computing, Engineering and Sciences, Sheffield Hallam University, <sup>1</sup>Greece <sup>2</sup>United Kingdom

#### 9 **1. Introduction**

10 Silicon carbide (SiC) particulate-reinforced aluminium matrix composites (AMC) are 11 attractive engineering materials for a variety of structural applications, due to their superior 12 strength, stiffness, low cycle fatigue and corrosion fatigue behaviour, creep and wear 13 resistance, compared to the aluminium monolithic alloys. An important feature of the 14 microstructure in the Al/SiC composite system is the increased amount of thermal residual 15 stresses, compared to unreinforced alloys, which are developed due to mismatch in thermal 16 expansion coefficients of matrix and reinforcement phases. The introduction of the 17 reinforcement plays a key role in both the mechanical and thermal ageing behaviour of the 18 composite material. Micro-compositional changes which occur during the thermo-19 mechanical forming process of these materials can cause substantial changes in mechanical 20 properties, such as ductility, fracture toughness and stress corrosion resistance.

The satisfactory performance of aluminium matrix composites depends critically on their integrity, the heart of which is the quality of the matrix/particle reinforcement interface. The nature of the interface depends in turn on the processing of the AMC component. At the micro-level, the development of local concentration gradients around the reinforcement can be very different to the nominal conditions. The latter is due to the aluminium alloy matrix attempt to deform during processing. This plays a crucial role in the micro-structural events of segregation and precipitation at the matrix-reinforcement interface.

27 28 29 The strength of particulate-reinforced composites also depends on the size of the particles, interparticle spacing, and the volume fraction of the reinforcement [1]. The microstructure 30 and mechanical properties of these materials can be altered by thermo-mechanical treatment 31 as well as by varying the reinforcement volume fraction. The strengthening of monolithic 32 metallic material is carried out by alloying and supersaturating, to an extent, that on suitable 33 heat treatment the excess alloying additions precipitates out (ageing). To study the 34 deformation behaviour of precipitate hardened alloy or particulate reinforced metal matrix 35 composites the interaction of dislocation with the reinforcing particles is much more 36 dependent on the particle size, spacing and density than on the composition [2]. 37 Furthermore, when a particle is introduced in a matrix, an additional barrier to the 38 movement of dislocation is created and the dislocation must behave either by cutting 39 through the particles or by taking a path around the obstacles [3].

1 2 3 4 5 6 7 8 9 At present, the relationship between the strength properties of metal matrix composites and the details of the thermo-mechanical forming processes is not well understood. The kinetics of precipitation in the solid state has been the subject of much attention. Early work on growth kinetics has been developed for the grain boundary case [4] and for intragranular precipitation [5]. These approaches have been integrated to produce a unified description of the inter- and intra-granular nucleation and growth mechanisms [6, 7]. More recently, successful attempts have been made to combine models of precipitate growth at interfaces with concurrently occurring segregation in aluminium alloys [8]. Studies of the relation between interfacial cohesive strength and structure have only recently become possible. This 10 is due to of remarkable advances in physical examination techniques allowing direct 11 viewing of interface structure and improved theoretical treatments of grain boundary 12 structure.

2

13 The ability of the strengthening precipitates to support the matrix relies on the properties of 14 the major alloying additions involved in the formation of these precipitates. The 15 development of precipitates in Al-based alloys can be well characterised through heat 16 treatment processing. Heat treatment affects the matrix properties and consequently the 17 strain hardening of the composite. Furthermore, the distribution and concentration of these 18 precipitates greatly affect the properties of the material where homogenous distribution of 19 small precipitates provides the optimum results.

20 The role of the reinforcement is crucial in the microdeformation behaviour. The addition of 21 SiC to aluminium alloy increases the strength and results in high internal stresses, in 22 addition to the ones caused by the strengthening precipitates. Furthermore, the SiC  $\overline{23}$ reinforced particles are not affected by the heat treatment process. A great deal of attention 24 has been recently devoted to understanding the strengthening mechanisms in metal matrix 25 composites, which are distinguished by a large particulate volume fraction and relatively 26 large diameter. Another important matter in understanding and modelling the strength of 27 particulate MMCs is to consider the effect of particle shape, size and clustering [9-11], as 28 29 well as the effects of clustering of reinforcement on the macroscopic behaviour and the effects of segregation to the SiC/Al interfaces [12]. Important role also play the effects of 30 casting condition and subsequent swaging on the microstructure, clustering, and properties 31 of Al/SiC composites [13].

32 33 34 Aluminium honeycomb sandwich panel constructions have been successfully applied as strength members of satellites and aircraft structures and also in passenger coaches of highspeed trains such as the TGV in France and the Shinkansen in Japan [14]. However, the cost 35 of producing the all welded honeycomb structure has been a key factor for not using this 36 technology on mass production rate. Recent developments in manufacturing methods have 37 given rise to a range of commercially viable metallic foams, one being Alulight. In 38 comparison to aluminium honeycomb core construction, metallic foams show isotropic 39 properties and exhibit non linear mechanical deformation behaviour. The metallic foams 40 have the potential to be used at elevated temperatures up to 200°C [15]. They also have 41 superior impact energy absorption and improved strength and weight savings. However, 42 the successful implementation of both aluminium honeycomb and metallic foam sandwich 43 panels for aerospace and transportation applications is dependent upon an understanding 44 of their mechanical properties including their resistance to fatigue crack growth and the 45 resistance of aluminium alloys to environmentally induced cracking or stress corrosion 46 cracking.

1 This chapter discusses first the relationship between the interfacial strength with the 2 thermo-mechanical deformation process and the resulting macroscopic mechanical 3 behaviour of particle-reinforced aluminium matrix composites. Micro-compositional 4 changes which occur during the thermo-mechanical processing of these materials can cause 5 substantial changes in mechanical properties such as ductility, fracture toughness, or stress 6 corrosion resistance. A mico-mechanistic model will be presented for predicting the 7 interfacial fracture strength in AMCs in the presence of magnesium segregation. Finally, the 8 use of powerful nondestructive evaluation tools, such as infrared thermography, will be 9 discussed to evaluate the state of stresses at the crack tip and to monitor fatigue crack 10 growth in particle-reinforced aluminium alloy matrix composites.

11 In the second part of the chapter the structural integrity of Aluminium Honeycomb (HC) 12 13 sandwich panels is compared with the new core material concept of aluminium foams. Aluminium Honeycomb sandwich panels are used to reduce weight whilst improving the 14 compressive strength of the structure with the aerospace industry being one of the prime 15 users of HC sandwich panels for structural applications. The cost of producing all welded 16 HC structures has been the key factor for not using this technology on a mass production 17 basis. An alternative to the aluminium honeycomb (HC) sandwich panels is the metallic 18 foam sandwich panel, which has been gaining interest in the same field. These foams are 19 anisotropic, exhibit non-linear mechanical behaviour, and they have the potential for use at 20 temperatures up to 200°C. They have superior impact energy absorption, and improved 21 strength and weight savings. The lower weight as compared to conventional solid wrought 22 aluminium alloys will mean a reduction in fuel consumption thus providing economical savings.

23 24 25 26 27 28 29 30 31 32 33 34 This chapter attempts to investigate whether aluminium honeycomb sandwich panels, with their homogenous hexagonal core can be successfully replaced by metallic foam sandwich panels, which have an inhomogeneous core. A successful replacement would improve the confidence of manufacturers in the exploitation of this new material in replacing traditional materials. Current levels of understanding of cyclic stressing in metallic foam sandwich panels is limited and models of long term understanding of this aspect of failure are very important for both aerospace and automotive sectors. Burman et al [16] suggests that fundamental fatigue models and concepts proven to work for metals can be applied to metallic foam sandwich panels. A study by Shipsha et al [17] investigated experimentally both metallic foam and other cellular foams, using compact tension specimens. Shipsha's et al research is extremely interesting and implies that a sandwich panel should be considered 35 36 37 whole and not two separate entities. Banhart and Brinkers has shown that it is very difficult to detect the features leading to fatigue failure in metallic foams due to the metallic foam being already full of micro cracks [18]. However, Olurin [19] investigation suggest that the 38 fatigue crack growth mechanism of Alulight and Alporas foam is of sequential failure of cell 39 faces ahead of crack tip. The main conclusion is that for a given  $\Delta K$ , the fatigue crack 40 propagation rate, da/dN decreases with increasing density and for a given stress intensity, 41 the fatigue crack propagation rate increases when the mean stress is increased.

42 Current levels of understanding of cyclic stressing in aluminium foams is limited and 43 models of long term understanding of this aspect of failure are important for both aerospace 44 and automotive sectors. This is particularly important for low-density foam and honeycomb 45 materials which despite thin ligament thickness, have good properties in compression. A 46 method of analysis is proposed to predict life expectancy of aluminium honeycomb and

47 metallic foam sandwich panels.

1

#### 2. SiC-particulate reinforced aluminium matrix composites

#### 2.1 Materials

2 3 4 5 6 7 8 9 10 Aluminium - silicon - magnesium alloys (A359) are important materials in many industrial applications, including aerospace and automotive applications. The alloys from the Al-Si-Mg system are the most widely used in the foundry industry thanks to their good castability and high strength to weight ratio. Materials based on A359 matrix reinforced with varying amounts of silicon carbide particles are discussed in this chapter.

Four types of material are used: 1) Ingot as received A359/40%SiC, with an average particle size of 19±1 micron, 2) Ingot as received A359/25%SiC, with an average particle size of 17±1 micron, 3) Hot rolled as received A359/31%SiC with an average particle size of 17±1 micron 11 and 4) Cast alloy as received A359/30%SiC with particles of F400grit, with an average 12 particle sizes of 17±1 micron. Table 1, contains the details of the chemical composition of the 13 matrix alloy as well as the amount of silicon carbide particles in the metal matrix

- 14 composites.
- 15

| TYPES           | Si  | Mg  | Mn  | Cu  | Fe  | Zn  | SiC |
|-----------------|-----|-----|-----|-----|-----|-----|-----|
| INGOT<br>A359   | 9.5 | 0.5 | 0.1 | 0.2 | 0.2 | 0.1 | 40  |
| INGOT<br>A359   | 9.5 | 0.5 | 0.1 | 0.2 | 0.2 | 0.1 | 25  |
| CAST<br>A359    | 9.5 | 0.5 | 0.1 | 0.2 | 0.2 | 0.1 | 30  |
| ROLLE<br>D A359 | 9.5 | 0.5 | 0.1 | 0.2 | 0.2 | 0.1 | 31  |

16 Table 1. Types and composition of the material

17 The microstructure of such materials consists of a major phase, aluminium or silicon and the 18 eutectic mixture of these two elements. In this system, each element plays a role in the 19 material's overall behaviour. In particular, Si improves the fluidity of Al and also Si particles 20 are hard and improve the wear resistance of Al. By adding Mg, Al - Si alloy become age

21 hardenable through the precipitation of Mg<sub>2</sub>Si particulates.

#### 2.2 Heat treatment

22 23 Properties in particulate-reinforced aluminium matrix composites are primarily dictated by 24 25 26 27 28 29 30 31 the uniformity of the second-phase dispersion in the matrix. The distribution is controlled by solidification and can be later modified during secondary processing. In particular, due to the addition of magnesium in the A359 alloy, the mechanical properties of this material can be greatly improved by heat treatment process. There are many different heat treatment sequences and each one can modify the microstructural behaviour as desired [20]. Precipitation heat treatments generally are low temperature, long-term processes. Temperatures range from 110°C to 195°C for 5 to 48 hours. The selection of the time temperature cycles for precipitation heat treatment should receive careful consideration. 32 Larger precipitate particulates result from longer times and higher temperatures. On the 33 other hand, the desired number of larger particles formed in the material in relation to their 34 interparticle spacing is a crucial factor for optimising the strengthening behaviour of the 35 composite. The objective is to select the heat treatment cycle that produces the most

- favourable precipitate size and distribution pattern. However, the cycle used for optimising one property, e.g. tensile strength, is usually different from the one required to optimise a
- different property, e.g. yield strength, corrosion resistance.
- Heat treatment of composites though has an additional aspect to consider, the particles
- $\begin{array}{r}
   1 \\
   2 \\
   3 \\
   4 \\
   5 \\
   6 \\
   7 \\
   8 \\
   9 \\
   10 \\
   \end{array}$ introduced in the matrix. These particles may alter the alloy's surface characteristics and
- increase the surface energies [21].
- The heat treatments were performed in Carbolite RHF 1200 furnaces with thermocouples
- attached, ensuring constant temperature inside the furnace. There were two different heat
- treatments used in the experiments, T6 and modified-T6 (HT-1) [21, 22].
- The T6 heat treatment consists of the following steps: solution heat treatment, quench and
- 11 age hardening (Fig. 1).
- 12



- 13
- 14 Fig. 1. T6 Heat treatment diagram showing the stages of the solution treatment for 2 hours 15 and artificial ageing for 5h

16 In the solution heat treatment, the alloys have been heated to a temperature just below the 17 initial melting point of the alloy for 2 hours at 530±5°C where all the solute atoms are 18 allowed to dissolve to form a single phase solid solution. Magnesium is highly reactive with 19 Silicon at this temperature and precipitation of Mg<sub>2</sub>Si is expected to be formed. The alloys 20 were then quenched to room temperature. In age hardening, the alloys were heated to an 21 intermediate temperature of 155°C for 5 hours where nucleation and growth of the  $\beta'$  phase. 22 The desired  $\beta$  phase Mg<sub>2</sub>Si precipitated at that temperature and then cooled at room 23 temperature conditions. The precipitate phase nucleates within the grains at grain 24 boundaries and in areas close to the matrix-reinforcement interface, as uniformly dispersed 25 particles. The holding time plays a key role in promoting precipitation and growth which 26 results in higher mechanical deformation response of the composite.

27 The second heat treatment process was the modified-T6 (HT-1) heat treatment, where in the 28 solution treatment the allovs have been heated to a temperature lower than the T6 heat 29 treatment, at 450±5°C for 1 hour, and then guenched in water. Subsequently the alloys were

- 30 heated to an intermediate temperature of 170±5°C for 24 hours in the age hardened stage
- 31 and then cooled in air (Fig. 2).





Fig. 2. Modified T6 (HT-1) showing stages of solution treatment for 1 hour and artificial ageing for 24h

4 In both heat treatments undesired formation of phases, like the  $Al_4C_3$ , is a possibility and 5 selection of the solution treatment as well as the age hardening processes should be 6 carefully considered. Temperature and time control, therefore, is extremely important 7 during heat treatment. If the melt temperature of SiC/Al composite materials rises above a 8 critical value,  $Al_4C_3$  is formed increasing the viscosity of the molten material, which can 9 result in severe loss of corrosion resistance and degradation of mechanical properties in the 10 cast composite; excessive formation of  $Al_4C_3$  makes the melt unsuitable for casting. In the 11 A359/SiC composite high silicon percentage added in excess aids to the formation of  $Al_4C_3$ , 13 since such oxides prevent the dissolution of SiC particles [22].

#### 14 2.3 Metallographic examination

In order to analyse the microstructure, a series of sample preparation exercises were carried out, consisted of the cutting, mounting, grinding and polishing of the samples. The microstructures were investigated by SEM, EDAX, and XRD to determine the Al/SiC area percentage, size and count of particulates.

19 The microstructures of the examined MMCs in the as received condition have four distinct 20 micro phases as clearly marked on the image micrograph, which are as follows: the 21 aluminium matrix, the SiC particles, the eutectic region of aluminium and silicon and the 22 Mg phase (Fig. 3). The distribution of SiC particles was found to be more or less uniform, 23 however, instances of particle free zones and particle clustered zones were observed. 24 Matrix-reinforcement interfaces were identified by using high magnification Nano-SEM. In

- Matrix-reinforcement interfaces were identified by using high magnification Nano-SEM. In the as received hot rolled images the Al Matrix/SiC reinforcement interface is clearly identified (Fig. 4). These interfaces attain properties coming from both individual phases of constituents and facilitate the strengthening behaviour of the composite material.
- In the modified T6 (HT-1) condition the microsturucture of the cast 30% SiC has the same phases as in the as received state, plus one rod-shape phase (Fig.5) along the matrix and at
- 30 the matrix-reinforcement interface has been identified to be Mg<sub>2</sub>Si precipitates in an early

 $\begin{array}{r}
 1 \\
 2 \\
 3 \\
 4 \\
 5 \\
 6 \\
 7 \\
 8 \\
 9 \\
 10 \\
 \end{array}$ stage which are not fully grown. This evidence shows that  $\beta$  phase has been formed with magnesium and silicon reacting together but  $\beta$  phases forming platelets of precipitates have not been formed in this HT-1 heat treatment, and this is probably due to the solution treatment temperature that did not allow enough reactivity time between the main alloying elements.

In the rolled 20% SiC the microstructure of HT-1 heat treatment shows an increase of the Silicon phase as shown in the image (Fig. 6). Silicon has been expanded during solidification

and subsequent ageing. This formed round areas around the whole area of the composite.

- Comparing with the cast 30% SiC sample, in the rolled material the silicon phase is



- 11
- 12 Fig. 3. Microstructure of cast 30% SiC in the as received condition showing four distinct
- 13 phases: Aluminium matrix, SiC particles, eutectic region of aluminium and silicon and Mg
- 14 phase
- 15



16

17 Fig. 4. Microstructure of rolled 31% SiC in the as received condition showing matrix-

18 reinforcement interfaces

1 increased by 6%. This increase under the same heat treatment conditions is explained by the 2 difference in the percentage of reinforcement in the material. Therefore, it becomes evident 3 that the introduction of SiC reinforcement promotes zone kinetics and phase formation 4 reactions during heat treatment process. The reinforcement, depending on its percentage in 5 the matrix material, accelerates or restrains events such as precipitation and segregation. 6 This is further supported by the fact that precipitation has not been observed in the HT-1 17 heat treated 20% SiC rolled material, where lower percentage of SiC reinforcement slowed-8 down the precipitation kinetics and  $\beta'$  phases could not be created in a similar manner as the 30% SiC cast sample.

10 In the T6 condition the microstructural results showed that in the rolled 31% SiC sample 11 precipitates of Mg<sub>2</sub>Si have been formed in the matrix in a platelet shape with a size of 12 around 1-3 μm, as well as in areas close to the interface (Fig. 7). The higher solution 13 temperature and lower age hardening holding time that exist in the T6 heat treatment 14 process, promoted the forming of this type of precipitates which more densely populated 15



- 17 Fig. 5. Microstructure of cast 30% SiC in the HT-1 condition showing rod shape  $\beta'$  phases of
- 18 Mg<sub>2</sub>Si around the matrix and the interface of the reinforcement
- 19

16

8



20

21 Fig. 6. Hot rolled HT-1 sample showing phases of Aluminium, SiC, Silicon, Mg

the interface region compared to the matrix. In the case of presence of a crack in the matrix, the precipitates act as strengthening aids promoting crack deflection at the interface resulting in an increase of the composite's fracture toughness [20, 23]. Furthermore, the precipitates formed in the matrix act as support to strengthening mechanisms of the reinforcement-matrix interface.



Fig. 7. (a) Hot rolled 31% SiC -T6 showing precipitate formed around the reinforcement.
(b) Hot rolled 31% SiC - T6 showing Mg<sub>2</sub>Si precipitates formed between the SiC reinforcement interface in a platelet shape of around 1-3 µm. A porous close to the interface has been identified in a similar size

13 The X-ray diffraction was carried out on the MMCs in the as received, as well as, in the heat 14 treatment conditions, in samples with 20%, 30% and 31% of SiC particulates. Even though 15 some peaks were superimposed, the results clearly showed the phases present in the 16 microstructures. In particular, in the as received condition and in the heat treatment 17 conditions the results showed existence of aluminium matrix material, eutectic silicon, SiC, 18 Mg<sub>2</sub>Si, SiO<sub>2</sub> phases as the distinct ones, and also MgAl<sub>2</sub>O<sub>4</sub> and Al<sub>2</sub>O<sub>3</sub> phases. MgAl<sub>2</sub>O<sub>4</sub> and 19 Al<sub>2</sub>O<sub>3</sub> oxides give good cohesion between matrix and reinforcement when forming a 20 continuous film at the interface. The presence of MgAl<sub>2</sub>O<sub>4</sub> (spinel) shows that low 21 percentage of magnesium reacted with SiO<sub>2</sub> at the surface of SiC and formed this layer in 22 the interphacial region between the matrix and the reinforcement.

$$2SiO_2 + 2Al + Mg \to MgAl_2O_4 + 2Si \tag{1}$$

The layers of  $MgAl_2O_4$  protect the SiC particles from the liquid aluminium during production or remelting of the composites. This layer provides more than twice bonding strength compared to  $Al_4C_3$ . Furthermore, the layer of  $Al_2O_3$  oxide is formed as a coating when SiO<sub>2</sub> is reacting with liquid aluminium.

 $28 \qquad \qquad 3SiO_2 + 4Al \rightarrow 2Al_2O_3 + 3Si \qquad (2)$ 

The same phases have been identified in the HT-1 modified condition. In the T6 condition XRD results showed one more phase present which is the spinel-type mixed oxide MgFeAl0<sub>4</sub> showing that Fe trace reacted with Mg and in the presence of aluminium and oxygen formed this oxide.

7 8

#### 2.4 Micro-hardness testing

1 2345678 The three samples have been compared in relation to their microhardness performance based on the reinforcement percentage, the heat treatment conditions and the different manufacturing forming processes. Microhardness of the three composites has been measured in order to get the resistance of the material to indentation, under localized loading conditions. The microhardness test method, according to ASTM E-384, specifies a range of loads using a diamond indenter to make an indentation, which is measured and converted to a hardness value [21, 22].

9 Measuring the different phases in the micro-level it is quite challenging, as the SiC 10 reinforcement of ≈17µm in size was not easy to measure, due to small indentation mark left 11 when a small load on the carbide is applied. When introducing higher values of load, the 12 indentation was not localized in the carbide but covered some of the matrix area too. The 13 load was finally set to 50 grams in order to obtain valid measurements coming from 14 different areas of the samples: SiC, aluminium matrix, and the overall composite i.e. areas 15 superimposing matrix and reinforcement.

16 There are many factors influencing the microhardness of a composite material, including the 17 reinforcement percentage, interparticle spacing and also particle size. Moreover, 18 manufacturing forming processes influence material's microhardness behaviour in relation 19 to the reinforcement percentages in the composites.

20 The cast sample in the as received condition has the highest MMC microhardness, where the 21 rolled 20% SiC with lower percentage of reinforcement has the lowest values. By altering the 22 microstructure with modified T6 (HT-1) heat treatment all values of the three samples show 23 an increase between 20-45% from the initial state (Fig. 8). This shows the effect of the heat 24 treatment in the micro-deformation of the matrix-reinforcement interface due to the 25 presence of precipitates and other phases and oxide layers. 26



27

28 Fig. 8. Microhardness values Vs. Heat treatment cycles for the MMC areas

29 In the T6 condition it was observed the larger increase in microhardness values from the as 30 received state, ranging from 20% to 90% depending on the reinforcement percentage and

123456789 manufacturing process. In particular, in the rolled 20% SiC material the increase in microhardness values is in the order of 90%.

- Furthermore, variability in microhardness values was observed when comparing cast and
- rolled materials with different percentage of SiC. However, this variability varied when
- samples processed at different heat treatment conditions were compared. Highest variability
- showed samples in the as received condition, whereas lowest variability showed samples in the T6 condition, with samples in the HT-1 condition in between. This can be explained by
- the fact that precipitates act as strengthening mechanisms and affect the micromechanical
- behaviour of the composite material.
- 10 In the absence of precipitates (in the as received condition), the volume percentage of SiC 11 and the manufacturing processing play a significant role in micromechanical behaviour of 12 the composite. As precipitates are formed due to heat treatment process they assume the 13 main role in the micromechanical behaviour of the material. In the HT-1 heat treatment 14 condition there is presence of  $\beta'$  precipitates which affect the micromechanical behaviour in 15 a lesser degree than in the case of T6 heat treatment condition where fully grown  $\beta$ 16 precipitates are formed. It becomes clear that after a critical stage, which if related to the 17 formation of  $\beta$  precipitates in the composite the dominant strengthening mechanism is 18 precipitation hardening.
- 19 While Figure 8 shows results in areas that include the interface region (where precipitates 20 are concentrated) Figure 9, shows results on microhardness values in the aluminium matrix 21 (where precipitates are dispersed). In Figure 9 there is similar variability for all three 22 materials processing states, as received, HT-1, and T6. This implies that in the matrix 23 material the percentage of the reinforcements, the manufacturing process, as well as the 24 precipitation hardening, are strengthening mechanisms of equal importance. 25



#### Microhardness Vs Heat Treatment-AL

26

27 Fig. 9. Microhardness Vs. Heat treatment cycles for Aluminium areas

28 Figure 10 shows microhardness measurements obtained from areas around the matrix-29 reinforcement interface in a composite heat treated in the T6 condition. The microhardness

values are higher in the close proximity of the interface. It is observed that cast material has higher values than the rolled material. In the case of rolled material, the microhardness raises as the percentage of reinforcement increases.



5

6 Fig. 10. Interfacial microhardness showing measurements obtained from areas close to the 7 matrix- reinforcement interface in the T6 condition

#### 8 **2.5 Tensile testing** 9 Aluminium – SiC r

Aluminium - SiC particulate composite samples were tested in tension for two different
volume fractions, 20% and 31%, in reinforcement [23]. The dog-bone coupons were tested
according to ASTM E8-04 in the as received and, following two different heat treatments,
modified T6 (HT-1) and T6 heat treatment conditions.. The mechanical properties of the
composites are presented in Table 2.

| 1 | 4  |
|---|----|
| т | т. |

| Material                   | Condition        | σ <sub>0.2</sub> (MPa) | $\sigma_{uts}(M\!\!Pa)$ | ε(%)            | E                 | $\mathrm{HV}_{0.5}$ |
|----------------------------|------------------|------------------------|-------------------------|-----------------|-------------------|---------------------|
| Rolled Al A359-<br>SiC-20p | T1<br>HT-1<br>T6 | 146<br>147<br>326      | 157<br>190<br>360       | 1.5<br>4<br>2.1 | 100<br>102<br>112 | 114<br>172<br>223   |
| Rolled Al A359-<br>SiC-31p | T1<br>HT-1<br>T6 | 158<br>155<br>321      | 168<br>187<br>336       | 1<br>2<br>1.3   | 108<br>110<br>116 | 150<br>182<br>236   |

15

16 Table 2. The mechanical properties of Al/SiC Composites

17 The engineering stress/strain curves of the composite are shown in Figure 11. As can be

18 clearly seen in Figure 11, the HT-1 heat treatment improved both the strength and strain to

19 failure than the untreated composites for both volume fractions. Furthermore, the failure

12

 $\begin{array}{r}
 1 \\
 2 \\
 3 \\
 4 \\
 5 \\
 6 \\
 7 \\
 8 \\
 9 \\
 10 \\
 \end{array}$ strain for this temper is considerably higher than for the T6 heat treatment; this may be attributed either to the nucleation of the  $\beta$  precipitate phases which although not yet visible, may lead to the increase of the plastic deformation through crack deflection mechanisms and/or to annealing which acts competitively to the precipitation leading to the toughening of the composite. However, the T6 heat treatment exhibits the highest strength followed by the HT-1 and the as received state. Finally, as was expected, the "as received" composites behaviour in tension deteriorates with increasing filler concentration.

The experiments showed that for the same range of conditions tested, the yield and the ultimate tensile strengths of the SiC/Al composites were mainly controlled by the percentage of reinforcement as well as by the intrinsic yield/tensile strengths of the matrix 11 alloys. The addition of the SiC reinforcement created stress concentrations in the composite, 12 and thus the aluminium alloy could not achieve its potential strength and ductility due to 13 the induced embrittlement. Composites in the as-received condition failed in a brittle 14 manner with increasing percentage of reinforcement. As a result, with increasing 15 reinforcement content, the failure strain of the composites was reduced as shown in Figure 16 11. From the above postulations it is obvious that the phase that dominates the mechanical 17 behaviour of the composite is the precipitation phase created by age hardening while the 18 reinforcement phase plays a secondary role.

19



#### 20

21 Fig. 11. Stress / Strain curves of Al/SiC Composites

22 The heat treatment affected the modulus of elasticity of the composites by altering the 23 24 transition into plastic flow (see Table 2 and Fig. 12). Composites in the T6 condition strained elastically and then passed into a normal decreasing-slope plastic flow. Composites tested in 25 26 27 28 29 the HT-1 condition exhibit a greater amount of strain than the as received and those heat treated in the T6 condition. The failure strain increasing from about 1.5% strain to about 4% but the greater influence was a sharper slope of the stress-strain curve at the inception of plastic flow.

This increase in elastic proportional strain limit and the steepening of the stress-strain curve

30 were reflected by the higher yield and ultimate tensile strengths observed in the heat-treated

31 composites. The increase in flow stress of composites with each heat-treatable matrix probably indicated the additive effects of dislocation interaction with both the alloy precipitates and the SiC reinforcement. The combination increased the strain in the matrix by increasing the number of dislocations and requiring higher flow stresses for deformation, resulting in the higher strengths observed. Ductility of SiC/Al composites, as measured by strain to failure, is again a complex interaction of parameters. However, the prime factors affecting these properties are the reinforcement content, heat treatment and precipitation hardening.



9

Materials - processing Conditions

Fig. 12. Young's Modulus vs. Processing Conditions curves showing T6 treated compositeshaving the highest modulus

#### 12 **2.6 Fracture toughness KIC testing**

13 The plane strain fracture toughness test involves the loading to failure of fatigue precracked, notched specimens in tension or in three-point bending. The calculation of a valid toughness value can only be determined after the test is completed, via examination of the load-displacement curve and measurement of the fatigue-crack length. The provisional fracture toughness value, K<sub>Q</sub>, is first calculated from the following equation:

18 
$$K_Q = \left(\frac{P_Q}{BW^{1/2}}\right) \cdot f\left(\frac{a}{W}\right) \tag{3}$$

19 where  $P_Q$  is the load corresponding to a defined increment of crack length, B is the 20 specimen's thickness, W is the width of the specimen, and  $f(\alpha/W)$  is a geometry dependent 21 factor that relates the compliance of the specimen to the ratio of the crack length and width, 22 expressed as follows:

23 
$$f\left(\frac{a}{W}\right) = \frac{(2+a/W)(0.86+4.64a/W-13.32a^2/W^2+14.72a^3/W^3-5.6a^4/W^4)}{(1-a/W)^{3/2}}$$
(4)

Only when specific validity criteria are satisfied, the provisional fracture toughness,  $K_Q$ , can be quoted as the valid plane strain fracture toughness,  $K_{IC}$ . The standard used for conducting this experiment, ASTM E399, imposes strict validity criteria to ensure that the plane strain conditions are satisfied during the test. These criteria include checks on the form and shape of the load versus displacement curve, requirements on specimen's size and crack geometry, and the 0.2% proof strength values at the test temperature. Essentially, these conditions are designed to ensure that the plastic zone size associated with the precrack is small enough so that plane strain conditions prevail, and that the linear elastic fracture mechanics approach is applicable.

10 Fracture toughness tests were conducted using a servo-hydraulic universal testing machine 11 with data acquisition controller. The system was operated on load control for the fatigue 12 13 pre-cracking stage, and on position control for the crack opening displacement (COD) testing. The fatigue test for pre-cracking was conducted at a frequency of 1 Hz, at a load 14 ratio R = 0.25 and load range of 3.7 - 4.5 KN according to the materials' ultimate tensile 15 strength. The COD was monitored by a clip gauge attached to the specimen with a testing 16 rate set at 1 mm/min. Moreover, a thermal camera was set for thermographic monitoring of 17 the crack opening displacement. Compact tension (CT) specimens were prepared for 18 fracture toughness tests according to ASTM E399. The thickness B of the specimens was 9.2 19 mm for the MMC, and 5 mm for the unreinforced aluminium alloys.

Provisional K<sub>Q</sub> values were calculated according to ASTM E399 standard for all specimens
 according to Equations (1) and (2), where Pq = Pmax. Load versus displacement curves for
 Al/SiCp composites and unreinforced aluminium alloys are shown in Fig. 13. Fracture
 toughness data for Al/SiCp and unreinforced aluminium alloys are summarised in Table 2.



25 26

24

Fig. 13. Load – Displacement curves for Al/SiCp composites subjected to T1, T6 and HT-1
 heat treatment conditions and three unreinforced aluminium alloy samples

| Material             | Heat   | E     | Rp0.2 | B    | a/W   | α <sub>eff</sub> | Ko    | Valid | Reason |
|----------------------|--------|-------|-------|------|-------|------------------|-------|-------|--------|
|                      | Treatm | (GPa) | (MPa) | (mm) |       | (mm)             | (MPa  |       |        |
|                      | ent    |       |       |      |       |                  | `√m)  |       |        |
| 2000 series Al       | AR.    | 71    | 75    | 5.10 | 0.552 | 27.62            | 55,36 | No    | 2**    |
| 2000 series Al       | AR.    | 71    | 78    | 5.13 | 0.555 | 26.76            | 56,00 | No    | 2**    |
| 2000 series Al       | AR.    | 71    | 72    | 5.00 | 0.558 | 28.43            | 58,48 | No    | 2**    |
| A359/SIC/31p         | T1     | 106   | 117   | 9.20 | 0.456 | 20.79            | 19,28 | Yes   | -      |
| A359/SIC/31p         | T6     | 108   | 120   | 9.21 | 0.462 | 20.12            | 22,05 | Yes   | -      |
| A359/SIC/31p         | HT1    | 116   | 157   | 9.20 | 0.467 | 21.33            | 20.75 | Yes   | -      |
| A357/SIC/20p<br>[16] | -      | -     | 215   | -    | -     | -                | 18.60 | -     | -      |
| A359/SIC/10p<br>[16] | -      | -     | 300   | -    | -     | -                | 17.40 | -     | -      |

\*\*Validity criteria:

1 Excessive crack curvature

2 Thickness criteria not satisfied 3 Excessive plasticity

4 a/W out of range

5 Non-symmetrical crack front

6 In plane crack propagation

2 Table 2. Fracture toughness data for Al/SiCp and Al alloys and test validity

As is shown in Table 2, Al/SiC<sub>p</sub> composites exhibited lower provisional K<sub>Q</sub> values than the reference unreinforced aluminium alloys. In addition, heat treatment processing, and especially T6 treated specimen, had the highest K<sub>Q</sub> values compared to the other two heat treatment conditions. According to the load-displacement curves in Figure 3, composites clearly showed more brittle behaviour than the unreinforced aluminium alloys. T6 heat treated composites have the highest strength, but the lowest ductility compared to the other materials. Although these results provide some insight regarding the fracture behaviour of the materials examined, specific validity criteria have to be satisfied in order to obtain K<sub>IC</sub> values.

#### 12 **2.7 Examination by infrared thermography**

13 Nondestructive evaluation techniques are powerful tools for monitoring damage in 14 composite materials [24]. Infrared thermography was used to monitor the plane crack 15 propagation behaviour of particulate-reinforced AMCs [25, 26]. The deformation of solid 16 materials is almost always accompanied by heat release. When the material becomes 17 deformed or is damaged and fractured, a part of the energy necessary to initiate and 18 propagate the damage is transformed in an irreversible way into heat [26]. The heat wave, 19 generated by the thermo-mechanical coupling and the intrinsic dissipated energy during 20 mechanical loading of the sample, is detected by the thermal camera. By using an adapted 21 detector, thermography records the two dimensional "temperature" field as it results from 22 the infrared radiation emitted by the object. The principal advantage of infrared 23 thermography is its noncontact, non-destructive character.

16

A rectangular area on the specimen, located just in front of the initial pre-cracking region, was selected, as shown in Fig. 14a.



4

1 2 3

5 Fig. 14.a CT specimen showing the selected area for thermographic monitoring

6 The development of fracture was monitored in that area using infrared thermography. The 7 8 mean temperature in this area versus time during crack growth was calculated using the recorded thermal imprint. As the specimen was stretched in tension, stresses were 9 accumulating in the specimen, and the temperature increased as a function of time. When 10 the accumulated energy became sufficient to propagate the crack, crack growth was 11 observed, resulting in the stress relief. This corresponded to a peak in the temperature-time 12 curve followed by a sudden decrease in temperature. As shown in Fig. 14b, 14c and 14d this 13 behaviour was recurrent until the failure of the specimen. In these figures the thermographic 14 monitoring of Aluminium 2xxx alloy, Al/SiCp T6 composite, and Al/SiCp HT1 composite 15 samples is presented respectively. The different stages of crack growth for each material up 16 to the final fracture of the specimen can be clearly observed. Just prior to fracture, the 17 plasticity zone was clearly delineated on the specimen's surface as a heated region, which 18 may be readily attributed to local plastic deformation. Furthermore, as seen in all figures, 19 the crack was propagated in-plane throughout the experiment.

20 A comparison of the thermography graphs in Figs. 14b, 14c, and 14d leads to the conclusion 21 that the aluminium alloy exhibited different crack propagation behaviour than the Al/SiCp 22 composites. For the aluminium alloy, the temperature versus time curve in Fig. 5b showed 23 extended plasticity behaviour before final fracture occurred. This behaviour was evidenced 24 by the constant increase in temperature between the temperature picks at the 60th and 140th 25 second (figure 14b). This behaviour may be attributed to the small specimen thickness. 26 However, for the T6 heat treated composite material in Fig. 14c, fracture was more elastic as 27 the multiple temperature peaks indicated a confinement of the plasticity zone. Also, 28 plasticity was formed in a more balanced way regarding the overall fracture process. It was 29 also observed that T6 heat treated composites exhibited fewer picks compared to the HT1 30 heat treated specimens (Fig. 14d). This was attributed to the presence of a stronger interface 31 in the T6 material as the accumulation of precipitates near the interface, resulted in the

32 improvement of the fracture toughness of the material.









3 Fig. 14. Thermographic monitoring of various CT specimens showing the different stages of

4 crack growth up to the specimen's final fracture: (b) Aluminium 2xxx, (c) Al/SiCp T6

5 composite, (d) Al/SiCp HT1 composite.

# 6 2.8 A model for predicting interfacial strengthening behaviour of particulate 7 reinforced AMCs 8 A model proposed by McMahon and Vitek [27] predicts the fracture resistance of 9 material that fails by an intergranular mechanism. Based on this model, an effect

A model proposed by McMahon and Vitek [27] predicts the fracture resistance of a ductile material that fails by an intergranular mechanism. Based on this model, an effective work 10 parameter can be developed to predict fracture strength of an interface at a segregated state 11 using Griffith crack-type arguments. The Griffith's equation, which was derived for elastic 12 body, is applied here because it is assumed that the yielding zone size ahead of the crack is 13 small enough and the fracture is governed by the elastic stress field. The model further 14 assumes that small changes in interfacial energy caused by segregation of impurities at the 15 interface will result in a much larger change in the work of fracture. This is due to the fact 16 that the work of fracture must be provided by a dislocation pile-up mechanism around the 17 advancing crack-tip on the interface. This implies that additional work must be provided to 18 deform the material at the crack-tip in addition to the work needed to overcome the 19 interface energy and to replace it with two surfaces. The definition of interfacial fracture 20 strength,  $\sigma_{int}$ , is then given by:

21 
$$\sigma_{\rm int} = \sqrt{\frac{100\varepsilon_P E_{\rm int}}{\pi d}}$$

22 where,

12

23 E is Young's modulus, d is the particle thickness, since it is assumed that cracks of the order

24 of the particle size are present when considering crack propagation through the interface

19

(5)

- and the particulate,  $\varepsilon_p$  is the energy required to create two fracture surfaces =  $2\varepsilon_s \varepsilon_{gb}$  (=  $\varepsilon_o$ ), with  $\varepsilon_s$ , the surface energy, and  $\varepsilon_{gb}$ , the grain boundary energy.
- 1 2 3 4 5 6 7 The 100  $\varepsilon_p$  component allows for dislocation interaction and movement ahead of the cracktip in ductile materials. This refers to the work required for a total separation of the lattice planes, which is equal to the area under the force-extension curve.
- From equation (6) ep can be estimated if Kint (Interface fracture toughness) and Eint
- (Interface Young's Modulus) are known.

$$\frac{K_{\text{int}}^2}{100E_{\text{int}}} = \varepsilon_p \left( 1 - \frac{ZRT\ln(1 - c + Bc)}{\varepsilon_p} \right)^n \tag{6}$$

- 9 Where,
- 10 Z, describes the density of interface sites which are disordered enough to act as segregation 11 sites (=  $D \rho_S$ ), with D the thickness of the interface region, and  $\rho_S$  the density of the interface
- 12 region (D=300 nm) ( $\rho$ = 2.6889 g/cm<sup>3</sup> for Aluminium and 3.22 g/cm<sup>3</sup> for SiC),
- 13 R, is the gas constant (= 8.314472(15) J•K-1•mol-1),
- 14 T, is the absolute temperature (= 803.15 K for T6, = 723.15 K for HT1),
- 15 c, is the segregate concentration needed to cause embrittlement (= 0.1 for pure aluminium),
- 16 B, describes the modification of the boundary energy by impurities using the Zuchovitsky 17 equations,
- 18 n, is the work hardening exponent (= 10 for FCC aluminium).
- 19 In hard particle reinforced metal matrix composites the stress transfer from the matrix to the 20 particles is mainly controlled by the misfit of the elastic constants between the two phases 21 [28]. To measure the stress transfer to the particle, in an homogeneous material subjected to 22 23 24 tensile loading, the stress carrying capability of the particle is defined as the ratio of the normal stress  $\sigma_N$  to the particle in the loading direction to the macroscopic tensile stress,  $\sigma_T$ , i.e. the ratio L =  $\sigma_N$  /  $\sigma_T$ . By using Eshelby's theory, the stress carrying capability of a 25 spherical inhomogeneity can be written as [29]:

26 
$$L = \frac{9x(2+3x)}{(1+2x)(8+7x)}$$
(7)

27 28 where,  $x = E_i / E_{m}$ , and  $E_i$  and  $E_m$  are Young's moduli for inhomogeneity and matrix, respectively.

29 Furthermore, the shear lag model, originally developed by Cox [30] modified by Llorca [31], 30 can be used to estimate the stress carrying capability of a particulate, assuming that the 31 volume fraction of reinforcement is small and the average stress in the matrix is 32 approximately equal to the applied stress:

 $L = 1 + \frac{a}{\sqrt{3}}$ 33 (8)

where  $a = \overline{h}/2\overline{r}$  is the aspect ratio of the reinforcement, with  $\overline{h}$  and  $\overline{r}$  the average length and the average diameter of the particle. 34 35

36 A model has been proposed to estimate the effects of particle volume fraction on fracture 37 toughness in SiC particle-reinforced aluminium alloy matrix composites. This model

38 assumes that SiC particles are uniformly distributed in the matrix and that the pattern of

12 particle distribution is similar to FCC structure in metals. The fracture toughness of the composite can then be written as [32]:

3 
$$K_{IC} = \frac{K_p}{L_p} V'_m + \frac{2K_{int}}{L_p + L_m} (V_m - V'_m) + \frac{K_m}{L_m} 2V_m + K_m (1 - 3V_m)$$
(9)

4 5 6 7 8 9 10 where  $K_{IC}$ ,  $K_p = 3$  MPa m-1/2,  $K_m = 35$  MPa m-1/2, and  $K_{int}$  is the fracture toughness of the composite, SiC particulates, A359 aluminium alloy matrix, and interface, respectively.  $L_p$ and  $L_m$  are the stress carrying capabilities of a particulate and the matrix, respectively. On average, for SiC particles and aluminium alloy matrix,  $L_p \sim L_m \sim 2$ . The value of  $L_m = 1$  is applicable for clean surfaces. However, due to processing conditions and the physical interaction at the matrix/reinforcement interface the interface contains partially contaminated surfaces, therefore  $L_m = 2$  since it cannot be considered as a "clean surface".  $V_m$  and  $(V_m-V'_m)$ 11 are the area fractions for particle cracking and interface failure, respectively. These area 12 fractions though are not accurately known. However Wang and Zhang [33] found that the 13 ratio of particle cracking over interface failure  $V_m/(V_m-V'_m)$  was about 0.13 (= 1.4%/10.7 %) 14 in a SiC particle-reinforced aluminium alloy composite.

15 Young's modulus of matrix has been obtained for A359 aluminium matrix. The particles  $E_{pr}$ 16

matrix E<sub>m</sub>, and interface E<sub>i</sub> shown in equation

$$E_{C} = E_{p} v_{f}^{2/3} + E_{m} \left( 1 - V_{f}^{\prime 2/3} \right) + E_{i} \left( V_{f}^{\prime 2/3} - V_{f}^{2/3} \right)$$
(10)

18 Due to the fact that the difference  $(V'_f - V_f)$  is very small, a good approximation is to 19 consider that the Young's modulus of the interface region is close to that of the matrix; 20  $E_i \cong E_m$  [32].

21 The parameter B describes the modification of the boundary energy by impurities using the 22 Zuchovitsky equations [34, 35], given by:

23 
$$B = e^{\left(\frac{\varepsilon_1 - \varepsilon_2}{RT}\right)} \cong e^{\left(\frac{0.75\varepsilon_F}{RT}\right)}$$
(11)

24 where  $\varepsilon_2 - \varepsilon_1$  is the difference between the formation energy in the impurity in the bulk and 25 the interface region. It is assumed that the values of the surface energy and the impurity 26 formation energy in the bulk are close, and therefore the numerator in the exponential term 27 depends on the impurity formation energy in the interface region, which is assumed to be 28 0.75  $\varepsilon_{f}$ , where  $\varepsilon_{f}$  is the formation energy of the impurity in the bulk.

- 29 Using Faulkner's approach [36], to the derivation of impurity formation energy,
- 30  $\varepsilon_{\rm f} = \varepsilon_{\rm s} + \varepsilon_{\rm e}$ (12)

31 where,  $\varepsilon_s$  is the surface energy required forming the impurity atom and  $\varepsilon_e$  is the elastic 32 energy involved with inserting an impurity atom into a matrix lattice site. This is given by:

33 
$$\varepsilon_f = \frac{0.5\varepsilon_s}{1.94} + \frac{8\pi G}{3e} a_m (a_i - a_m)^2 eV$$
(13)

34 where,

17

35  $\varepsilon_{\rm S}$  is the surface energy (1.02 J m-2)

- e is the electronic charge (1.60217646 \*10^19 Coulomb)
- a<sub>i</sub> is the impurity atomic radius (0.118 nm for Si)

- a<sub>m</sub> is the matrix atomic radius (0.143 nm for aluminium)
- G is the shear modulus (26 GPa for aluminium)
- By performing the calculations the impurity formation energy,  $\varepsilon_{fr}$  for A359 aluminium alloy (Al-Si-Mg) can be determined and then substituted in equation (11) to calculate B.
- 1 2 3 4 5 6 7 8 9 The micro-mechanics model described above is based on thermodynamics principles and is used to determine the fracture strength of the interface at a segregated state in aluminium matrix composites. This model uses energy considerations to express the fracture toughness 10 of the interface in terms of interfacial critical strain energy release rate and elastic modulus. 11 The interfacial fracture toughness is further expressed as a function of the macroscopic 12 fracture toughness and mechanical properties of the composite, using a toughening 13 mechanism model based on stress transfer mechanism. Mechanical testing is also performed 14 to obtain macroscopic data, such as the fracture strength, elastic modulus and fracture 15 toughness of the composite, which are used as input to the model. Based on the 16 experimental data and the analysis, the interfacial strength is determined for SiC particle-17 reinforced aluminium matrix composites subjected to different heat treatment processing 18 conditions and the results are shown in table 2. It is observed that K<sub>int</sub> values are close to the 19  $K_{1c}$  values of the composites. Furthermore,  $\sigma_{int}$  values found to be dependent on the heat 20 treatment processing with T6 heat treatment composite obtain the highest interfacial 21 fracture strength.

#### 22 23 2.9 Fatigue testing and crack growth behaviour

- Tension-tension fatigue tests were conducted using a hydraulic testing machine. The system 24 was operated under load control, applying a harmonic tensile stress with constant 25 amplitude. By specifying the maximum and the minimum stress levels, the other stress 26 parameters could be easily determined. These were the stress range,  $\sigma_{r}$ , stress amplitude,  $\sigma_{a}$ , 27 mean stress,  $\sigma_m$ , and fatigue stress ratio, R (= $\sigma_{min}/\sigma_{max}$ ). Throughout this study, all fatigue 28 tests were carried out at a frequency of 5 Hz and at a stress ratio R = 0.1. Different stress 29 levels between the ultimate tensile strength (UTS) and the fatigue limit were selected, 30 resulting in so-called Wöhler or S-N curves. Tests exceeding 10<sup>6</sup> cycles without specimen 31 failure were terminated. Specimens that failed in or close to the grips were discarded. The 32 33 34 geometry of the samples was the same as those used for the tensile characterisation, i.e. rectangular strips of 12.5mm width, and 1.55mm thickness.
- The normalised "S-N" curves of the fatigue response of the Al/SiC composites is shown in 35 36 37 Fig. 15. The stress was normalised over the UTS of each material and plotted against the number of cycles to failure. As can be observed, whereas in the untreated T1 condition the composite retains at least 85% of its strength as fatigue strength, the corresponding value for 38 the T6 heat treatment is falling to the 70% of UTS. The HT1 heat treatment is exhibiting an 39 intermediate behaviour, with its fatigue strength falling to 75% of the corresponding UTS 40 value. It can be concluded that aggressive heat treatment reduces the damage tolerance of 41 the composites.
- 42 A direct comparison of the fatigue performance of the composite with the corresponding 43 quasi static performance in tension reveals that the T6 heat treatment improved the strength
- 44 of the composite. This can be attributed to a dominant mechanism related to the changes in
- 45
- the microstructure of the composite. This mechanism relates to the precipitations appearing

in the microstructure of the composite at the vicinity of the interphase area, which results to the composite hardening. The creation of the interphase together with the improved stress transfer may be regarded as the main contributing parameters to the improved mechanical properties of the particulate reinforced composite. The improved static strength is followed by a less spectacular performance in fatigue, with the fatigue limit of the material falling to the 70% of the UTS.

S-N Curve Al/SiC 20%



#### 8 9

Fig. 15. S-N Curve of Al/SiC 20% Composite

#### 10 2.9.1 Crack growth rate vs. range of stress intensity

11 To study the crack growth rate (da/dN) vs. stress intensity range  $(\Delta K)$  data for aluminium 12  $SiC_p$  composites and aluminium 2xxx series specimens, the materials were subjected to 13 cyclic loading. Fatigue crack growth tests were conducted according to the ASTM E647 14 standard using a servo hydraulic testing machine. The tests were conducted under load 15 control. Compact tension (CT) specimens were prepared for the fatigue crack growth 16 experiments. The fatigue tests for the monolithic aluminium specimens were performed at a 17 standard frequency of 5 Hz. However, a lower frequency of 1 Hz was selected for the 18 composite specimens in order to minimize the effect of sudden failure due to the brittle 19 nature of these materials. The experiments were performed at a load ratio R = 0.25 and 20 maximum load ranges of 3.7 - 4.5 KN, keeping the maximum stress at about 70% of the 21 material's ultimate tensile strength.

The technique used for determining the crack growth rate versus stress intensity range during the cyclic loading tests was based on non-contact monitoring of the crack propagation by lock-in thermography. This new technique deals with mapping the crack growth nondestructively. Lock-in thermography is based on remote full field monitoring of thermal waves generated inside the specimen by cyclic loading that caused an oscillating exact time dependence between the output signal (thermal wave) and the reference input signal (fatigue cycle). This is done with a lock-in amplifier so that both phase and magnitude images become available.

 $\begin{array}{r}
 1 \\
 2 \\
 3 \\
 4 \\
 5 \\
 6 \\
 7 \\
 8 \\
 9 \\
 10 \\
 \end{array}$ The detection system included an infrared camera. The camera was connected with the lockin amplifier, which was then connected to the main servo hydraulic controller. Therefore, synchronization of the frequency through the lock-in amplifier and the mechanical testing machine could be achieved and lock-in images and data capture during the fatigue testing were enabled.

The camera was firstly set at a distance close to the specimen, in order to have the best possible image capture. Then, the fatigue pre-cracking started while synchronizing, at the 11 same frequency, fatigue cycles and infrared camera through the lock-in amplifier.

12 13 In order to determine the crack growth rate and calculate the stress intensity factor using thermographic mapping of the material undergoing fatigue a simple procedure was used: 14

- The distribution of temperature and stresses at the surface of the specimen was a) monitored during the test. Therefore, thermal images were obtained as a function of time and saved in the form of a movie.
- The stresses were evaluated in a post-processing mode, along a series of equally spaced b) reference lines of the same length, set in front of the crack-starting notch. The idea was that the stress monitored at the location of a line versus time (or fatigue cycles) would exhibit an increase while the crack approaches the line, then attain a maximum when the crack tip was on the line. Due to the fact that the crack growth path could not be predicted and was not expected to follow a straight line in front of the notch, the stresses were monitored along a series of lines of a certain length, instead of a series of equally spaced points in front of the notch. The exact path of the crack could be easily determined by looking at the stress maxima along each of these reference lines.

Four lines of the same length, equally spaced at a distance of 1 mm, were set on the thermal images of the CT specimen at a distance in front of the specimen's notch.

23 24 25 26 27 28 29 30 31 32 33 34 35 36 In Figure 16, the crack growth rate for the heat treated composite specimens and the reference aluminium alloy samples are plotted on a logarithmic scale as a function of the stress intensity range. The results showed that the heat treatment processing influences crack growth behaviour of the composite materials. Specimens subjected to T6 heat treatment condition exhibited the highest crack growth rate vs. stress intensity range slope compared to the other composite systems. Moreover, the crack growth rate vs. stress intensity range line of specimens subjected to T6 heat treatment was shifted towards higher  $\Delta K$  values compared to that from specimens subjected the other two heat treatment conditions. This implies that in order to attain the same crack growth rate, higher stress 37 intensity factor is required for specimens subjected to T6 condition compared to those 38 subjected to T1 and HT-1 conditions. The need for higher stresses for a crack to propagate 39 reveals the material's microstructural strength, where micro-mechanisms such as 40 precipitation hardening promote high stress concentrations at the crack tip, resulting in the 41 toughening of the crack path. The above postulations agree with previews results, where the 42 T6 heat treated composites showed superior strength but the lowest ductility compared to 43 T1 or HT-1 heat treated specimens. Results, shown in Figure 16, indicate that at intermediate 44 values of crack growth rate (10-2 to 10-5 mm/cycle) the Al/SiCp composites have fracture 45 properties comparable to those of the unreinforced matrix alloys. It is obvious that in these 46 composites crack propagation rate seems more balanced and takes more time than the 47 aluminium alloy obtaining crack growth rate values from around 10-1 to 10-4 mm/cvcle.

24

15

16

17

18

19

20

21





#### 2.9.2 Estimation of da/dN vs. ΔK using thermography and compliance methods

3456789 Using the procedure described above based on thermographic mapping, the local stress versus time was measured for the T6 heat treated Al/SiCp along each of the four reference lines placed in front of the CT specimen's notch. The maximum value of stress versus the number of fatigue cycles was then plotted for those four lines (Figure 17). As expected, Figure 17 shows that the local stress, monitored at the location of each line, increases as the crack is approaching that line, then attains a maximum when the crack tip is crossing the 10 line. Finally, after the crack has crossed the line, the local stress measured at the location of 11 the line decreases. This is also expected, since the stress values shown in Figure 17 are stress 12 maxima from all the locations along the particular line. At the exact position on a line where 13 the crack has just crossed, the local stress is null as expected.

14 From the stress maxima versus fatigue cycles curves, for each reference line, shown in 15 Figure 17, the crack lengths versus the number of fatigue cycles were determined for 16 A359/SiC<sub>P</sub> composites in all three different thermal treatment conditions: T1, T6, and HT-1 17 (Fig. 18). As it is shown in Figure 18, the crack growth rate was found to be quite linear for 18 all heat treatments. Also, there is a small change in the linear slope for the HT-1 heat treated 19 sample, showing increased ductility, which indicates that more time (i.e. cycles) is needed 20 for the crack to grow in this case. For the T6 heat treatment, the results depict a brittle 21 22 23 24 behaviour, as the crack starts to grow earlier than in the other two cases, supporting evidence of brittle fracture.

- The stress intensity range was further calculated by the data shown in Figure 17.  $\Delta K$  values have been estimated from the stress maxima versus fatigue cycles curves for each reference 25 line, shown in Figure 17. Each of the four lines provides a stress intensity range and a 26 da/dN value. The data obtained using lock-in thermography, shown in Figures 18 and 19, 27
- were correlated with crack growth rate values obtained by the conventional compliance 28 method and calculations based on the Paris law. Furthermore, the da/dN vs.  $\Delta K$  curves

steaming from the compliance method were plotted in the same graph, for comparison purposes, with those obtained using lock-in thermography (Fig. 20). It can be seen in Figure 20 that the two different methods are in agreement, demonstrating that lock-in thermography is a credible nondestructive method for noncontact evaluation of the fracture behaviour of materials.













Fig. 19. Crack growth rate determined by compliance vs. thermography for A359/SiCp composite

4



5 6

Fig. 20. da/dN vs. ΔK for Al/SiCp specimens - Thermography vs. Compliance method

1

#### 3. Aluminium honeycomb sandwich panels and metallic foam

#### 3.1 Material and experimental procedure

The compact tension specimens were manufactured from rectangular plates conforming to BS 7448-1: 1991 as shown in Fig. 21.



### 6

7 Fig. 21. Compact Tension Specimen

8 The fatigue tests were performed on a standard Mayes machine attached to a Pd system. 9 The Pd system was switched on with the current circulating for 30 minutes before any 10 readings were taken; the fatigue cycle was then begun. Data from the Pd system was 11 exported into an excel spreadsheet and the number of cycles versus crack propagation was 12 then plotted. From these results, values of stress intensity ( $\Delta K$ ) versus crack growth rate 13 were then calculated. In order to calculate the stress intensity factor, a standard equation 14 was used.

$$\Delta K = \frac{\Delta PY}{B\sqrt{W}} \tag{14}$$

16 Where, Y = geometry factor,  $\Delta P =$  change in cyclic load ( $P_{max} - P_{min}$ ), B = sample thickness 17 and W = sample width. Fatigue tests were conducted in fully tension - tension and at a

18 constant frequency.

#### 1 3.2 Results and discussion

The results of fatigue testing of aluminium honeycomb sandwich panel both in air and in 3.5% sodium chloride solution, are plotted in Figure 22. A total of twenty cyclic deformation tests were conducted in fully tension-tension at a constant frequency of 2HZ, which is equivalent to two cycles per second. The results of fatigue testing of metallic foam sandwich panel both in air and in 3.5% sodium chloride solution, are plotted in Figure 23.





8

9 Fig. 22. Aluminium Honeycomb Fatigue Data

10



11

12 Fig. 23. Metallic Foam Fatigue Data

#### 13 3.2.1 Aluminium honeycomb

Cyclic deformation data reveals that honeycomb sandwich panel samples do produce consistent results with acceptable repeatability of results even though the honeycomb core is not a conventional structure due to its complex geometry, but because of its homogeneity, it does compare well to the consistent results we would expect from a less complex conventional aluminium solid sample. The results, also, revealed that samples taken from a longitudinal direction constantly have a longer life expectancy, of approximately 40%, then

20 those samples taken from a transverse direction regardless of environmental exposure.

Plotting of fatigue data versus stress intensity for aluminium honeycomb sandwich panels shows that samples tested in a corrosive environment are inferior in performance when compared to samples tested in air. Evidence from crack propagation testing establishes that crack propagation takes place, firstly, within the side plate, leading to some fracture but mainly tearing of the honeycomb structure, only a small amount of crack propagation is evident in the honeycomb structure. The weakest part of the sandwich panel structure appears to be the interface between the aluminium side plate and honeycomb core, with the adhesive used being epoxy resin. Crack propagation testing shows that crack growth is not equal on both sides of the sandwich panel structure; this effect must be due to the complex geometry of the hexagonal core and is a potential difficulty when considering the commercial applications of the aluminium honeycomb sandwich panels.

This research produces a valid method of calculating the Paris exponent, m, with the aluminium honeycomb sandwich panel having a Paris exponent, m, of 1.9. This value is similar when compared to typical values for aluminium alloys of between 2.6 to 3.9.

#### 15 3.2.2 Metallic foam

16 Examination of the metallic foam sandwich panel revealed that a consistent form of failure 17 could not be established, with size and position of voids within the metallic foam core 18 having a detrimental effect on failure. Cyclic deformation data revealed that samples tested 19 in air produced inconsistent results showing that the voids within the metallic foam play an 20 important part in crack propagation. However, when samples are tested in an environment, 21 22 23 24 25 26 27 28 samples taken from the longitudinal direction are superior. This leads to the conclusion that in an environment precipitates within the outer skin have a significant effect on crack propagation. The crack deformation data suggests that due to the complexity of the metallic foam structure and the scatter of results the life of samples exposed to a corrosive environment cannot be correlated with data produced in air. Analysis shows that this is simply untrue and if the two sets of data are plotted a lower and upper trend can be produced, independent of environment and rolling direction, and it is possible to establish a trend of crack growth data within the two bands. This research produced a valid method of 29 calculating the Paris exponent, m. The metallic foam sandwich panel had a Paris exponent, 30 m, of 7.41.

#### 31 **3.3 A proposed method of analysis to predict the fatigue life of sandwich panels** 32 The method of analysis is formed by acquiring the experimental data for alum

The method of analysis is formed by acquiring the experimental data for aluminium honeycomb and metallic foam sandwich panels. This experimental data is then compared to data produced by calculating the number of cycles to failure. The aim is to calculate the fatigue lives observed experimentally for both aluminium honeycomb and metallic foam sandwich panels. The calculated data will then be used to produce an equation that will predict experimental fatigue life for the complex metallic foam sandwich panels. Conventionally, crack growth rate can be related to the stress intensity factor range using equations (15) and (16).

$$\Delta K = Y(\Delta P)\sqrt{\pi a}$$
(15)

41 
$$\frac{da}{dN} \equiv C(\Delta K)^m \tag{16}$$

1 By rearranging equation (15) and (16) and separating variables and integrating for  $m \neq 2$  gives,

3

7

$$N_f = \frac{2}{(m-2)C(Y\Delta P\sqrt{\pi})^m} \left(\frac{1}{ai^{(m-2)/2}} - \frac{1}{a_f^{(m-2)/2}}\right)$$
(17)

Before equation (17) could be solved to calculate residual life from a crack size ( $a_i$ ) one must know the final or critical crack size ( $a_j$ ). For the critical crack condition when  $a = (a_j)$  equation (15) can be rewritten as;

$$a_f = \frac{1}{\pi} \left( \frac{K_c}{Y P_{\max}} \right)^2 \tag{18}$$

8 Where; K<sub>c</sub>= Fracture Toughness

9 The fracture toughness of aluminium honeycomb sandwich panels is 0.91 MPa  $\sqrt{m}$  and 0.85

10 MPa  $\sqrt{m}$  for Alulight foam. The calculated crack propagation life versus experimental crack

11 propagation life is shown in Figure 24. In Fig. 24 data can be seen for aluminium honeycomb

12 sandwich panels. The graph clearly shows an excellent correlation between calculated and

13 experimental results.

14



15

16 Fig. 24. Calculated Crack Propagation Life versus experimental Crack Propagation Life for

17 Aluminium Honeycomb Sandwich Panel



Fig. 25. Calculated Crack Propagation Life versus experimental Crack Propagation Life for
 Metallic Foam Sandwich Panels

However, the calculated crack propagation life versus experimental crack propagation life for metallic foam sandwich panel is shown in Fig. 25 where it can be clearly seen that calculated data does not correlate with experimental data. The graph illustrates that calculated data always produces a higher number of cycles to failure for metallic foam sandwich panels. The main reason for this is that calculation of stress within the metallic foam structure is complex due to the inhomogenity of the voids within the foam. Equations produced using data from Figs. 24 and 25 were then used to calculate experimental data equation for foam:

12 Foam Calculated:

 $\sigma = -0.072 \ln N_f + 1.5518 \tag{19}$ 

14 Honeycomb calculated:

15

13

 $\sigma = -0.0912 \ln N_f + 1.3589 \tag{20}$ 

16 Therefore, to plot experimental foam data:

17 
$$\sigma = \frac{(-0.1632 \ln N_f - 2.9107)}{2}$$
(21)



2 Fig. 26. Calculated Fatigue Life versus Experimental Fatigue Life for Metallic Foam and 3 Aluminium Honeycomb Sandwich Panels

4 The results of both aluminium honeycomb and metallic foam data for both calculated and 5 6 7 8 experimental cycles to failure is shown in Figure 26. An equation was calculated for each set of data, equations 19 for metallic foam and 20 for aluminium honeycomb respectively. The equations 19 and 20 can then be used to develope an equation 21 to predict the fatigue life of a close cell metallic foam sandwich panel. Using equation 21, calculated life for 9 aluminium honeycomb and metallic foam sandwich panels are compared with original 10 experimental data. What is clear from the Fig. 28 is that all of the experimental data for the 11 two types of specimens correlate with the predicted values. The data correlation proves that 12 a successful model is produced to calculate fatigue life for metallic foam sandwich panels. 13 This model is of extreme importance because it shows that from a structural point of view, 14 metallic foam sandwich panels can successfully replace aluminium honeycomb sandwich

15 panels.



34

Fig. 27. Showing Fatigue Data for Aluminium Honeycomb, Metallic Foam Sandwich Panel
 and Calculated Model Data

#### 4 4. Concluding remarks

5 The influence of processing conditions in the micromechanical behaviour of Al/SiC 6 composites has been discussed. Two different manufacturing processes (cast and rolled), 7 three reinforcement percentages (20%, 30%, 31%) and three processing states (as received, 8 HT-1, T6 heat treated) have been compared.

9 The importance of processing conditions in the micro-structural events of segregation and 10 precipitation has been depicted at the micro/nano level using microhardness measurements 11 and nano-scale phase identification of the matrix-reinforcement interface, and the 12 developments of strengthening mechanisms in the composite have been identified. The HT-13 1 heat treatment condition clearly showed an increase in the microhardness, due to  $\beta$ 14 precipitates as well as other phases and oxides formed in the composite. T6 heat treatment 15 showed the highest microhardness values due to formation of  $\beta$  precipitates, which 16 contribute to strengthening of the interface.

17 Microhardness and tensile testing results show that the composite micro-mechanical 18 behaviour is influenced by certain factors. In the absence of precipitates (as received state) or 19 in the case of dispersed precipitates (aluminium matrix) the dominant parameters 20 influencing the micromechanical behaviour of the composite are the reinforcement 21 percentage, the interparticle distance and the mean size of particulates. However, when 22 precipitates are concentrated in the areas close to the interface (T6 condition) these 23 precipitates contribute to the strengthening of the composite material.

24 The thermographic examination of the materials show that heat treated composite samples 25 exhibit regular crack propagation behaviour. Stress concentration, due to the presence of 26 particle reinforcements, produced controlled crack growth and higher stresses, which were related to regular energy release by the material during fracture, indicative of brittle fracture behaviour. On the other hand, the large plastic deformation of the aluminium alloy can be associated with the absence of stress-peaks in conjunction with the monotonic temperature rise for a large part of the temperature / time curve prior to the specimen failure.

1 2 3 4 5 6 7 8 9 A model has been applied to predict the interfacial fracture strength of aluminium in the presence of silicon segregation. This model considers the interfacial energy caused by segregation of impurities at the interface and uses Griffith crack-type arguments to forecast the energy change in terms of the coincidence site stress describing the interface and the formation energies of impurities at the interface. Based on Griffith's approach, the fracture 10 toughness of the interface was expressed in terms of interfacial critical strain energy release 11 rate and elastic modulus. The interface fracture toughness was determined as a function of 12 the macroscopic fracture toughness and mechanical properties of the composite using two 13 different approaches, a toughening mechanism model based on crack deflection and 14 interface cracking and a stress transfer model. The model shows success in making 15 prediction possible of trends in relation to segregation and interfacial fracture strength 16 behaviour in SiC particle-reinforced aluminium matrix composites. The model developed 17 here can be used to predict possible trends in relation to segregation and the interfacial 18 fracture strength behaviour in metal matrix composites. The results obtained conclude that 19 the role of precipitation and segregation on the mechanical properties of Al/SiCp 20 composites is crucial, affecting overall mechanical behaviour.

21 The tension-tension fatigue properties of Al/SiC composites as a function of heat treatment 22 have been discussed as well as the associated damage development mechanisms. The 23 composites exhibited endurance limits ranging from 70% to 85% of their UTS. The T6 24 composites performed significantly better in absolute values but their fatigue limit fell to the 25 70% of their ultimate tensile strength. This behaviour is linked to the microstructure and the 26 good matrix-particulate interfacial properties. In the case of the HT1 condition, the weak 27 interfacial strength led to particle/matrix debonding. In the T1 condition the fatigue 28 behaviour is similar to the HT1 condition although the quasi static tensile tests revealed a 29 less ductile nature.

30 The crack growth behaviour of particulate-reinforced metal matrix composites was also 31 investigated. Aluminium A359 reinforced with 31% of SiC particles subjected to two 32 33 different thermal treatments, as well as wrought aluminium 2xxx series specimens, have been examined using thermographic mapping. Heat treated composites, and especially 34 those samples subjected to T6 aged condition, exhibited different behaviour of crack 35 propagation rate and stress intensity factor range than the as-received composite specimens. 36 Furthermore, the composite specimens exhibited different fatigue crack growth rate 37 characteristics than the base aluminium alloy samples. It becomes evident that the path of 38 fatigue crack growth depends on the heat treatment conditions, where crack propagation 39 relies on strengthening mechanisms, such as precipitation hardening. The microstructure of 40 the interphase region was also found to play a significant role in the crack growth behaviour 41 of particulate-reinforced composites. In this sense, T6 heat treated Al/SiCp composite

- 42 samples exhibits better interphase bonding behaviour than the other composite systems.
- 43 The fatigue crack growth curves reveal an approximately linear, or Paris law region, fitting 44 the function  $da/dN = C \Delta K$ . Crack growth rate vs. stress intensity range curves have been
- 45 obtained using lock-in thermography. These results are in agreement with crack growth rate
- 46 measurements using the conventional compliance method and calculations based on the

- Paris law. It becomes, therefore, evident that lock-in thermography has a great potential for evaluating nondestructively the fracture behaviour of metallic composite materials.
- Finally, cyclic deformation data reveals that metallic foam sandwich panel samples do not
- 1 2 3 4 5 6 7 produce consistent results with acceptable repeatability of results but by using calculated crack propagation life data and experimental data for both aluminium honeycomb and
- metallic foam sandwich panels a method of analysis has been proposed to predict fatigue
- life of metallic foam sandwich panels.

#### 8 References

9

10

11

12

13

14

15

16

17

18

19

20

21

22 23

24

25

37

38

39

40

41

42

- [1] K.G. Kreider, Composite Materials, in: Metallic Matrix Composites, Volume 4, Academic Press, New York and London (1974).
- [2] D.J. Llovd, Particle Reinforced Aluminium and Magnesium Matrix Composites, Int. Mater. Rev. 39, 1-23 (1994).
- [3] N.F. Mott and F.R.N. Nabarro, An attempt to estimate the degree of precipitation hardening, with a simple model, Proc Phys Soc 52, 85 (1940).
- [4] H.B. Aaron and H.I. Aaronson, Growth of grain boundary precipitates in Al-4% Cu by interfacial diffusion, Acta Meter. 16, 789 (1968).
- [5] H.B. Aaron, D. Fainstein and G.R. Kotler, Diffusion-Limited Phase Transformations: A Comparison and Critical Evaluation of the Mathematical Approximations, J. Appl. Phys. 41(11), 4404-4410 (1970).
- [6] H.R. Shercliff and M.F. Ashby, A process model for age hardening of aluminium alloys -I. The model, Acta Mater. 38, 1789-1802 (1990).
- [7] R.A. Carolan and R.G. Faulkner, Grain boundary precipitation of M23C6 in an austenitic steel, Acta Mater. 36, 257-266 (1988).
- [8] S.T. Hasan, J.H. Beynon and R.G. Faulkner, Role of segregation and precipitates on interfacial strengthening mechanisms in SiC reinforced aluminium alloy when subjected to thermomechanical processing, J. Mater. Process. Technol. 153-154, 757-763 (2004).
- [9] M. Manoharan and J.J. Lewandowski, In-situ Deformation Studies of an Aluminum Metal-Matrix Composite in a Scanning Electron Microscope, Scr. Metall. 23, 1801-1804 (1989).
- [10] M. Manoharan and J.J. Lewandowski, Effect of Reinforcement Size and Matrix Microstructure on the Fracture Properties of an Aluminum Metal-Matrix Composite, Mater. Sci. Eng. A 150, 179-186 (1992).
- [11] S.T. Hasan, Effect of heat treatment on interfacial strengthening mechanisms of second phase particulate reinforced aluminium alloy, 14th International Metallurgical and Materials Conference (Metal 2005), Hradec nad Moravici, Czech Republic, (2005).
- [12] J.J. Lewandowski, C. Liu and W.H. Hunt Jr., Effects of Microstructure and Particle Clustering on Fracture of an Aluminum Metal Matrix Composite, Mater. Sci. Eng. A 107, 241-255 (1989).
- [13] G. Rozak, J.J. Lewandowski, J.F. Wallace and A. Altmisoglu, Effects of Casting Conditions and Deformation Processing on A356 Aluminum and A356-20% SiC Composites, J. Compos. Mater. 26(14), 2076-2106 (1992).
- 43 [14] Bitzer T.1997 Honeycomb Technology: materials, design, manufacturing, applications 44 and testing. Chapman & Hall.
- 45 [15] Alulight International GmbH

- [16] Burman, M and Zenkert D, 1997, Fatigue in Foam Core Sandwich Beams International Journal of Fatigue, Vol 19, Issue 7, pp 551 -561
- [17] Shipsha, A, Burman, M and Zenkert, D. 1999, On Mode I Fatigue Crack Growth in Foam Core Materials for Sandwich Panels. Journal of Sandwich Structures and Materials Vol 2, Issuse 2, pp 103-116
- [18] Banhart, J and Brinkers, W, 1999, Fatigue Behaviour of Aluminium Foams, Journal of Materials Science Letters, 18:pp 617-619
- [19] Olurin, OB, McCullough, Fleck NA and Ashby MF, 2001, Fatigue crack Propagation in Aluminium Alloy Foams International Journal of Fatigue, Vol 23, Issue 5, pp 375-382
- [20] Myriounis D. P., S. T. Hasan, N. M. Barkoula, A. Paipetis, T. E. Matikas, "Effects of heat treatment on microstructure and the fracture toughness of SiCp/Al alloy metal matrix composites", Journal of Advanced Materials, vol. 41(3), pp. 18-27 (2009).
- [21] Myriounis D. P., S. T. Hasan and T. E. Matikas, "Influence of Processing Conditions on the Micro-Mechanical Properties of Particulate-Reinforced Aluminium Matrix Composites", Advanced Composites Letters, vol. 17(3), pp. 75-85 (2008).
- [22] Myriounis D. P., S. T. Hasan and T. E. Matikas, "Microdeformation behaviour of Al-SiC Metal Matrix Composites", Composite Interfaces, vol. 15(5), pp. 485-514 (2008).
- [23] Myriounis D. P., S. T. Hasan and T. E. Matikas, "Heat Treatment and Interface Effects on the Mechanical Behaviour of SiC-Particle Reinforced Aluminium Matrix Composites", Journal of ASTM International – JAI, vol. 5(7), published on-line, DOI: 10.1520/JAI101624 (2008).
- [24] D. G. Aggelis, E. Z. Kordatos, T. E. Matikas, "Acoustic Emission for Fatigue Damage Characterization in Metal Plates", Mechanics Research Communications", Mechanics Research Communications, vol. 38, pp. 106–110 (2011).
- [25] E. Z. Kordatos, D. P. Myriounis, S. T. Hasan, T. E. Matikas, "Monitoring the fracture behavior of SiCp/Al alloy composites using infrared lock-in thermography", Proceedings of SPIE - The International Society for Optical Engineering, Vol. 7294, Article number 72940X, 2009.
- [26] Myriounis D. P., E.Z. Kordatos, S. T. Hasan, T. E. Matikas, "Crack-tip stress field and fatigue crack growth monitoring using infrared lock-in thermography in SiCp/Al alloy composites", Strain, published on-line, DOI: 10.1111/j.1475-1305.2009.00665.x (2010).
- [27] C. J. McMahon Jr., V. Vitek, Effects of segregated impurities on intergranular Fracture Energy, Acta Metall, 27(4), 507-513 (1979).
- [28] L. Shoyxin, S. Lizhi, L. Huan, L. Jiabao, W. Zhongguang, Stress carrying capability and interface fracture toughness in SiC/6061 Al model materials, Journal of materials science letters 16, 863–869 (1997).
- [29] X. Q. Xu, D. F. Watt, Basic role of a hard particle in a metal matrix subjected to tensile loading, Acta Metal. Mater., 42(11), 3717-3729 (1994).
- [30] H. L. Cox, The elasticity and strength of paper and other fibrous materials, Br. J. Appl. Phys., 3, 72-79 (1952).
- [31] J. Llorca, An analysis of the influence of reinforcement fracture on the strength of discontinuously- reinforced metal matrix composites, Acta Metall. Mater., 43(1), 181-192 (1995).
- [32] Myriounis D. P., S. T. Hasan, T. E. Matikas, "Predicting interfacial strengthening behaviour of particulate reinforced MMC - A micro-mechanistic approach", Composite Interfaces, vol. 17(4), pp. 347–355 (2010).

| Recent Trends in Ca | asting,Welding and | d Degradation of | Aluminium | Alloys |
|---------------------|--------------------|------------------|-----------|--------|
|---------------------|--------------------|------------------|-----------|--------|

| [33] Z. Wang | g, R. J. Zhang,     | Microscopic    | characteristics | of fatigue    | crack  | propagation i   | n  |
|--------------|---------------------|----------------|-----------------|---------------|--------|-----------------|----|
| alur         | ninium alloy base   | ed particulate | e reinforced me | etal matrix c | omposi | ites, Acta meta | 1. |
| mate         | er., 42(4), 1433-14 | 45 (1994).     |                 |               |        |                 |    |

- [34] R. G. Faulkner, Impurity diffusion constants and vacancy binding energies in solids, Mater. Sci. Technol., 1(6), 442–447 (1985).
- [35] Hasan ST, Beynon JH, Faulkner RG., Role of segregation and precipitates on interfacial strengthening mechanisms in SiC reinforced aluminium alloy when subjected to thermomechanical processing, Journal of Materials Processing Technology 153-154:758-764 (2004).
  - [36] R. G. Faulkner, L. S. Shvindlerman, Grain Boundary Thermodynamics, Structures and Mechanical Properties, Materials Science Forum, 207-209, 157-160 (1996).